Drypower

VRLA AGM MULTIPURPOSE RANGE
BACKUP & MAIN POWER

6V

2.8Ah

SLA

AGM

6SB2.8P

Rechargeable AGM Sealed Lead Acid Battery

SP	EC	IFIC	CAT	10	NS

Nominal Voltage		6V
Nominal Capacity		
20 hour rate	(0.140A to 5.25V)	2.8Ah
10 hour rate	(0.266A to 5.25V)	2.66Ah
5 hour rate	(0.476A to 5.1V)	2.38Ah
1C	(2.8A to 4.8V)	1.587Ah
3C	(8.4A to 4.8V)	1.12Ah

Weight Approx. 570g

Internal Resistance (at 1KHz) Approx. $22m\Omega$

Maximum Discharge Current (5 secs) 42A

Charge Methods at 25°C

Cycle Use Charging Voltage Coefficient -5.0mV/°C/Cell	7.20V to 7.50V
Maximum Charging Current	0.84A
Standby Use Float Charging Voltage Coefficient -3.0mV/°C/Cell	6.75V to 6.90V

Operating Temperature Range

Charge	−15°C to 40°C
Discharge	−15°C to 50°C
Storage	-15°C to 40°C
Charge Retention (Shelf Life) at 20°C	
1 month	92%

 1 month
 92%

 3 months
 90%

 6 months
 80%

Case Material ABS UL94 HB

Termination F1 (Faston Tab 187)

Design Life 3-5 Years


Classified as a non-spillable battery. Approved for transportation by:

- Air (IATA/ICAO provision A67)
- Road
- Sea (per IMDG Special Provision 238)

Barcode









DIMENSIONS


mm (inch)








Drypower

CHARACTERISTICS CHARTS









FEATURES & BENEFITS

- Industry leading 99.99% pure lead content for superior service life and dependable performance.
- Maintenance free technology and non-spillable design.
- Excellent charge retention in storage.
- Higher percentage of tin content compared with the industry standard. Tin extends battery standby life by minimising sulphation (corrosion) especially at higher temperatures.
- Manufactured by Kung Long Battery (KLB) at facilities in Taiwan and Vietnam.

KLB is a leading manufacturer and complies with relevant international quality standards including ISO9001, CE ETL9000, UL1989, OHSAS18001 and ISO17025.

KLB supports Green Sustainable supply chain practices.









Aug2020

Performance may vary depending on application. All specifications are correct at time of creation. All specifications and operation conditions contained in this datasheet are subject to change or improvement without prior notice to the user. This data is for evaluation purposes only. No guarantee is intended or implied by this data. For clarification and updated information, please contact us.